



# reyberry 3A 720

PROPERTIES	VALUE	UNIT	STANDARD
<b>Dimensional characteristics</b>			
Nominal Thickness	180	µm	ISO 4591
<b>Mechanical properties</b>			
Tensile strength at break			
MD	24	MPa	ISO 527-3
TD	23	MPa	ISO 527-3
Tensile strain at break			
MD	600	%	ISO 527-3
TD	650	%	ISO 527-3
Impact resistance (Dart test F50)			
Flat area	800	g	ISO 7765-1
Fold area	600	g	ISO 7765-1
<b>Optical properties</b>			
Visible light transmission	90	%	EN 2155-5
Haze	62	%	EN 2155-9
IR effectiveness	85	%	EN 13206
<b>Other properties</b>			
Durability (*)	3	years	
Maximum Sulphur content	2000	ppm	EN 13206
Maximum Chlorine content	150	ppm	EN 13206
<b>Manufacturing country</b>	Spain		

(\*) At a climate of 130 - 160 kLangley/year (for different radiation conditions or different thickness, we should be consulted)

The information contained herein is based upon data to be reliable and is, to the best of our knowledge and belief, accurate. We offer it with our best intention, but as we cannot control a bad use of it, we shall not be liable for any loss, damage or injury that may occur from the use of this information. This information is not a product specification, which appears on the respective contracts and/or orders.

ID 288 STD - 17.05.2022



Reyvenvas, S.A.  
Autovía Sevilla-Málaga, Km. 5  
Polígono Industrial La Red  
41500 Alcalá de Guadaíra (Sevilla) España  
T. (+34) 95 563 15 40  
[comercial@reyvenvas.com](mailto:comercial@reyvenvas.com)

