



# reyberry 1C 360

PROPERTIES	VALUE	UNIT	STANDARD
<b>Dimensional characteristics</b>			
Nominal Thickness	90	µm	ISO 4591
<b>Mechanical properties</b>			
Tensile strength at break			
MD	25	MPa	ISO 527-3
TD	23	MPa	ISO 527-3
Tensile strain at break			
MD	480	%	ISO 527-3
TD	590	%	ISO 527-3
Impact resistance (Dart test F50)			
Flat area	670	g	ISO 7765-1
Fold area	500	g	ISO 7765-1
<b>Optical properties</b>			
Visible light transmission	92	%	EN 2155-5
Haze	46	%	EN 2155-9
IR effectiveness	70	%	EN 13206
<b>Other properties</b>			
Durability (*)	1	seasons	
Maximum Sulphur content	500	ppm	EN 13206
Maximum Chlorine content	50	ppm	EN 13206
<b>Manufacturing country</b>	Spain		

(\*) At a climate of 130 - 160 kLangley/year (for different radiation conditions or different thickness, we should be consulted)

The information contained herein is based upon data to be reliable and is, to the best of our knowledge and belief, accurate. We offer it with our best intention, but as we cannot control a bad use of it, we shall not be liable for any loss, damage or injury that may occur from the use of this information. This information is not a product specification, which appears on the respective contracts and/or orders.

ID 256 STD - 17.05.2022



Reyvenvas, S.A.  
Autovía Sevilla-Málaga, Km. 5  
Polígono Industrial La Red  
41500 Alcalá de Guadaíra (Sevilla) España  
T. (+34) 95 563 15 40  
[comercial@reyvenvas.com](mailto:comercial@reyvenvas.com)

 @reyvenvas  
 @reyvenvas  
 @reyvenvas\_sevilla



**reyvenvas**

[www.reyvenvas.com](http://www.reyvenvas.com)