



# reyfilm negro BB 3A

## black mulch film

PROPERTIES	VALUE	UNIT	STANDARD
<b>Dimensional characteristics</b>			
Nominal Thickness	100	µm	ISO 4591
<b>Mechanical properties</b>			
Tensile strength at break			
MD	22	MPa	ISO 527-3
TD	21	MPa	ISO 527-3
Tensile strain at break			
MD	570	%	ISO 527-3
TD	640	%	ISO 527-3
Tear strength			
MD	580	cN	ISO 6383-2
TD	820	cN	ISO 6383-2
Impact resistance (Dart test F50)			
Flat area	380	g	ISO 7765-1
<b>Optical properties</b>			
Relative light transmission	< 1	%	EN 13655
<b>Other properties</b>			
Durability (*)	3	years	

(\*) At a climate of 140 - 160 kLangley/year (for different radiation conditions or different thickness, we should be consulted).

The information contained herein is based upon data to be reliable and is, to the best of our knowledge and belief, accurate. We offer it with our best intention, but as we cannot control a bad use of it, we shall not be liable for any loss, damage or injury that may occur from the use of this information. This information is not a product specification, which appears on the respective contracts and/or orders.

ID 97 STD - 11.11.2022



Reyenvas, S.A.  
Autovía Sevilla-Málaga, Km. 5  
Polígono Industrial La Red  
41500 Alcalá de Guadaíra (Sevilla) España  
T. (+34) 95 563 15 40  
[comercial@reyenvas.com](mailto:comercial@reyenvas.com)

 @reyenvas  
 @reyenvas  
 @reyenvas\_sevilla

  
GRUPO  
armando  
alvarez



reyenvas

[www.reyenvas.com](http://www.reyenvas.com)